


CLIENT: Reliance Industries Limited

REGRESSION ANALYSIS ACCORDING TO ISO 9080 OF THE PE PIPE COMPOUND RELENE 46GP003 B



INTRODUCTION

Bodycote Polymer offers accredited testing and evaluation according to ISO 9080, i.e. hydrostatic pressure testing followed by evaluation of the long-term hydrostatic strength and MRS-classification according to ISO 12162.

TASK

The aim was to evaluate the compound according to ISO 9080 in order to obtain a MRS-classification according to ISO 12162 of the PE pipe compound Relene 46GP003 B from Reliance Industries Limited.

RESULTS OBTAINED

The evaluation was performed in accordance with ISO 9080:2003. The 4-parameter model gave the best fit. More information can be found in Bodycote Report P-09/26

EXTRAPOLATED STRENGTH VALUES

Temp [°C]	Time [Yrs]	σ_{LPL} [MPa]	σ_{LTHS} [MPa]
20	50	10.46	10.79
20	100	10.32	10.66
60	6.00	6.58	6.84
80	1.00	5.11	5.32

CLASSIFICATION

MRS = 10 MPa

CONTACT

Phone +46 155 22 14 76
Fax +46 155 26 31 25
Email info@bodycotepolymer.com
Web www.bodycotepolymer.com, www.bodycotetesting.com